

AMENDMENTS TO THE CLAIMS

1-10 (Cancelled)

11. (Currently amended) A fiber comprising starch, wherein the fiber has ~~a size ranging from about 0.02 dtex to about 5 dtex and a Tg of at least about -30°C~~ an average fiber diameter of less than 10 μ m.
12. (Previously presented) The fiber according to Claim 11 wherein the fiber comprises from about 20% to about 99.99% by weight of the fiber of starch.
13. (Previously presented) The fiber according to Claim 11 wherein the fiber further comprises a plasticizer.
14. (Previously presented) The fiber according to Claim 13 wherein the plasticizer selected from the group consisting of: sorbitol, monosaccharides, disaccharides, glycerol, polyvinyl alcohol, polyethylene glycol and mixtures thereof.
15. (Previously presented) The fiber according to Claim 13 wherein the plasticizer is present in the fiber at a level of from about 5% to about 70% by weight of the fiber.
16. (Previously presented) The fiber according to Claim 11 wherein the fiber further comprises a cross-linking agent.
17. (Previously presented) The fiber according to Claim 16 wherein the cross-linking agent is selected from the group consisting of: polyamide-epichlorohydrin resins, urea-formaldehyde resins, glyoxylated polyacrylamide resins, melamine formaldehyde resins, polyethylenimine resins, dialdehyde starch resins and mixtures thereof.
18. (Previously presented) The fiber according to Claim 16 wherein the cross-linking agent is present in the fiber at a level of from about 0.1% to about 10% by weight of the fiber.
19. (Cancelled)
20. (Previously presented) A fibrous structure comprising a plurality of fibers, wherein at least one fiber is a fiber according to Claim 11.

21. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has an absorbency ranging from about $1 \frac{\text{g Water}}{\text{g Dry Structure}}$ to about $15 \frac{\text{g Water}}{\text{g Dry Structure}}$.
22. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a total flexibility ranging from about 1.0 g/cm to about 75 g/cm.
23. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a geometric mean dry tensile strength ranging from about 10 g/cm to about 1200 g/cm.
24. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has an initial geometric mean wet tensile strength ranging from about 2 g/cm to about 400 g/cm.
25. (Previously presented) The fibrous structure according to Claim 24 wherein the fibrous structure has an initial geometric mean wet tensile strength ranging from about 2 g/cm to about 200 g/cm.
26. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a geometric mean decayed wet tensile strength ranging from about 0 g/cm to about 20 g/cm.
27. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a basis weight ranging from about 10 g/m^2 to about 450 g/m^2 .
28. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has an apparent density ranging from about 0.04 g/cm^3 to about 0.12 g/cm^3 .
29. (Currently amended) A paper product comprising a fibrous structure, wherein the fibrous structure comprises a fiber comprising starch, wherein the fiber has ~~a size ranging from about 0.02 dtex to about 5 dtex and a Tg of at least about -30°C~~ an average fiber diameter of less than 10 μm .
30. (Currently amended) A fibrous structure comprising a fiber comprising starch, wherein the fiber has ~~a size ranging from about 0.02 dtex to about 5 dtex and a Tg of at least about -30°C~~ an average fiber diameter of less than 10 μm and wherein the fibrous structure has a basis weight ranging from about 10 g/m^2 to about 450 g/m^2 .
31. (New) The fiber according to Claim 11 wherein the fiber is a melt blown fiber.
32. (New) The fiber according to Claim 11 wherein the fiber is a spunbond fiber.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.